



Legend

Brick Type A
Weinerberger Ashington Red
Multi

Brick Type B
Weinerberger Durham Red
Multi

Roof Tile 1
Weinerberger Calderdale Edge
Light Grey

Rev	Date	Comments	By

ACCOMMODATION SCHEDULE							
House type	Number	Mid	End	Det	Sqft	Bed Nos.	En-SU Total Sqft
Yew	17	6	11	0	755	2	No 12835
Holly	16	2	14	0	911	3	No 14576
Oak	6	0	1	5	914	3	Yes 5484
Willow	10	4	6	0	1164	4	Yes 11640
TOTAL	49						44535
Gross Area	2.48	Acres					
Nett Area	16.618	Sqft/Acre					
Coverage	18.3	UFA					
Density							

Stonebond

Stonebond Properties (Manchester)Ltd
Registered Office:
Suite 5, Egerton House
Towers Business Park
Wilmslow Rd
Didsbury, M20 2DX

site:

Edenfield Rd
Norden
Rochdale

title:

Materials Layout

scale:
(BA) 1:500
date:
Jun 23

drawing no:

SBM-001-ML01

sheet no:

Sheet 1 of 1

drawn by:
SMC
checked:

revision:

50 m

25 m

15 m

7.5 m

5 m

2.5 m

0 m

SCALE BAR 1:500

Ashington Red Multi

Product Technical Information Sheet


Wienerberger Code	24240070
Production Plant	Todhills
Manufacture	Soft Mud Moulded Stock
Configuration	Frogged
Colour	Red Multi
Appearance	Flat
Work Size (mm)	215 x 102.5 x 65
Pack Quantity	500 No.
Individual Dry Brick Weight (kg)	2.3

Technical Properties to BS EN 771-1

Size Tolerance (Mean/Range)	T1/R1
Gross Dry Density (kg/m ³ /Tolerance)	1630(D1)
Compressive Strength (N/mm ²)	≥20
Thermal Conductivity (W/(m·K)) $\lambda_{10, dry, unit}$ value (EN 1745 tabulated: S1)	P=90% 0.60
Durability Designation	F2
Water Absorption (%)	≤14
Initial Rate of Water Absorption (kg/(m ² ·min))	Min. 1.2 Max. 2.8
Active Soluble Salts	S2
Reaction to Fire	Class A1

Issue Date: 15/09/2020

Technical data correct at time of issue. Individual dry brick weights can vary and are for guidance only. Any questions regarding this data should be referred to the Wienerberger Technical Department. Due to the limitations of screen and print colour representation of product images it is advised that brick samples are viewed prior to ordering.



**BIM Objects
Download**



1000+ products to choose from



Expert help and advice



Comprehensive Design Services



Technical Support

Durham Red Multi Stock

Product Technical Information Sheet



Wienerberger Code	24240440
Production Plant	Todhills
Manufacture	Soft Mud Moulded Stock
Configuration	Frogged
Colour	Red
Appearance	Flat
Work Size (mm)	215 x 102.5 x 65mm
Pack Quantity	500 No.
Individual Dry Brick Weight (kg)	2.3

Technical Properties to BS EN 771-1

Size Tolerance (Mean/Range)	T1/R1
Gross Dry Density (kg/m ³ /Tolerance)	1630 (D1)
Compressive Strength (N/mm ²)	≥20
Thermal Conductivity (W/(m·K)) $\lambda_{10, dry, unit}$ value (EN 1745 tabulated: S1)	P=90% 0.60
Durability Designation	F2
Water Absorption (%)	≤14
Initial Rate of Water Absorption (kg/(m ² ·min))	Min. 1.2 Max. 2.8
Active Soluble Salts	S2
Reaction to Fire	Class A1

Issue Date: 15/09/2020

Technical data correct at time of issue. Individual dry brick weights can vary and are for guidance only. Any questions regarding this data should be referred to the Wienerberger Technical Department. Due to the limitations of screen and print colour representation of product images it is advised that brick samples are viewed prior to ordering.



**BIM Objects
Download**

