

Stone sample – cutting out - mortar for brickwork sample – removal of loose stone facings



Joints cut out to the facing stonework




Joints cut out to the decorative facing stonework



Loose/spalling stone removed and face cut back to shed water. Edge contrast to be softened using a conservative DOFF cleaning



Sample of Etherow Stone - Buff



Pointing to the brickwork in 1 part NHL3.5 Hydraulic lime, 2 parts builders sand and 1 part fine plastering sand



--.